MAGNETIC AND STRUCTURAL TRANSITIONS IN HELIMAGNETIC YMn_2O_5 J. G. Lin^{1,2} and T. C. Han¹¹Center for Condensed Matter Sciences, National Taiwan University, Taipei, 106, Taiwan²Center for Nanostorage Research, National Taiwan University, Taipei, 106, Taiwan

Introduction

In recent years, magnetic ferroelectric materials has been the subject of extensive studies due to their interesting magnetic and electric properties that reveal mutual correlations between magnetic and ferroelectric ordering [1]. Among them, YMn_2O_5 compounds are of particular interest for their unique nature of multiferroism. In this work, we prepare two YMn_2O_5 samples with different phases, one is orthorhombic (OR) and another is hexagonal (HX) structure, for investigating the structure dependency of magnetic properties.

Experiment

Two samples of the YMn_2O_5 compounds were prepared by solid-state reaction method. A stoichiometric mixture of high purity Y_2O_3 and Mn_2O_3 powders was ground and heated at 900 °C for 2 h. The reactant was reground, palletized and sintered at 1100/1400 °C in air for 16 h. The crystal structures and magnetic properties of the samples were examined by X-ray diffraction (XRD) and physical property measurement system (PPMS), respectively.

Results and discussion

XRD patterns of YMn_2O_5 compounds are shown in Fig. 1. By changing the sintering temperature from 1100 to 1400 °C, crystalline phases transforms from OR (the bottom pattern) to HX (the upper pattern).

Fig. 1 XRD patterns of YMn_2O_5 with two different phases.

The temperature-dependent magnetizations $M(T)$ were measured in a magnetic field of $H = 500$ Oe with zero-field-cooling (ZFC) and field-cooling (FC) modes. The $M_{\text{ZFC}}(T)$ and $M_{\text{FC}}(T)$ of HX and OR phases are shown in Fig. 2 and Fig. 3, respectively. Compare Fig. 2 with Fig. 3, we find that the magnitude of magnetic moment in HX phase is one order higher

than that of OR phase. Furthermore, the $M_{\text{ZFC}}(T)$ and $M_{\text{FC}}(T)$ show a splitting around 40 K for both samples, indicating a common feature of spin-glass/spin-canted state.

Fig. 2 Zero-field-cooled and field-cooled temperature dependence of magnetization for YMn_2O_5 sample with HX phase. Fig. 3 Zero-field-cooled and field-cooled temperature dependence of magnetization for the YMn_2O_5 sample with OR phase.

Figs. 4 and 5 are the field-dependent magnetization $M(H)$ curves of two samples at 10 and 100 K. It is observed that HX sample (see Fig. 4) is more ferromagnetic than OR sample.

Fig. 4 Magnetic hysteresis loop for the hexagonal YMn_2O_5 compound. Fig. 5 Magnetic hysteresis loop for the orthorhombic YMn_2O_5 compound.

Conclusion

We have prepared two YMn_2O_5 samples with different phases, one is hexagonal and another is orthorhombic. Based on the the results of temperature-dependent magnetization and low temperature $M-H$ curves, these two samples display a common feature of spin-glass/spin-canted state at low temperature and the sample with hexagonal structure is more ferromagnetic than that of orthorhombic structure.

References

[1] N. Hur *et al.*, Nature 429, 392 (2004).

*This project is financially sponsored by National Science Council (grand no. NSC 93-2752-M-002-007) and Ministry of Economics (grand no. 93-EC-17-A-08-S1-0006).